



## Gold Leaf – German

Crocodile Brand gold leaf average thickness is 0.3 to 0.8 microns.



Rosa-Noble & Patent 23.75kt ♦  
CR23.75RN AW = 20g  
98.9% Gold - .5% Silver  
.6% Copper



Dukaten & Patent 23.5kt ♦ ■  
CR23.50DK AW = 18.5g  
98% Gold – 1% Silver  
1% Copper



Sonnengold 23kt ♦  
CR23.00SG AW = 18g  
95.5% Gold – 1.5% Silver  
3% Copper



French Red 23kt  
CR23.00FR AW = 18g  
97% Gold – 3% Copper



23kt Double & Patent ♦ ■  
CR23.00DB AW = 18g  
95.5% Gold – 3.5% Silver  
1% Copper



Antique Gold 22.75kt  
CR22.75AG AW = 18g  
94.8% Gold – 3.2% Silver  
2% Copper



22kt Surface & Patent ♦ ■  
CR22.00SF AW = 16g  
92% Gold – 6.5% Silver  
1.5% Copper



Moon Gold 21kt  
CR21.00MG AW = 19.5g  
89% Gold – 5.2% Silver  
5.8% Palladium



Pale Gold 15.3kt  
CR15.30PL AW = 16g  
63.8% Gold – 36.2% Silver



White 12kt ♦ ■  
CR12.00WH AW = 16g  
50% Gold – 50% Silver



Silver Thin  
CR00.00ST AW = 25-30g  
100% Silver



Palladium ♦  
CR00.00PD AW = 20g  
100% Palladium



White 9kt ♦  
CR9.00WH AW = 16g  
49% Gold – 51% Silver



Platinum White  
CR00.PT/420 AW = 17.5g  
Gold - Silver - Platinum



Platinum Metal White  
CR00.PT/526 AW = 17.5g  
Gold - Silver - Palladium

Loose leaf oil Gilded on white paper. The ♦ indicates leaf that is also available in patent form.

AW = Average total weight (gold + alloy) indicated in grams per 1000 leaves.

The ■ indicates leaf that is available as Ribbon Gold.