

# Gold Leaf German



Rosa-Noble & Patent 23.75kt ♦☀  
CR23.75RN AW = 19g  
98.9% Gold - .5% Silver  
.6% Copper



French Red 23kt  
CR23.00FR AW = 18g  
97% Gold - 3% Copper




22kt Surface & Patent ♦ ■  
CR22.00SF AW = 16g  
92% Gold - 6.5% Silver  
1.5% Copper




Pale Gold 15.3kt  
CR15.30PL AW = 16g  
63.8% Gold - 36.2% Silver



Silver Thin  
CR00.00ST AW = 25-30g  
100% Silver



Dukaten & Patent 23.5kt ♦■☀  
CR23.50DK AW = 18g  
98% Gold - 1% Silver  
1% Copper



23kt Double & Patent ♦■☀  
CR23.00DB AW = 18g  
95.5% Gold - 3.5% Silver  
1% Copper



Moon Gold 21kt  
CR21.00MG AW = 20g  
89% Gold - 5.2% Silver  
5.8% Palladium



White 12kt ♦ ■  
CR12.00WH AW = 16g  
50% Gold - 50% Silver



Palladium Glass ♦☀  
CR00.PG/80 AW = 16g  
100% Palladium



Sonnengold 23kt ♦  
CR23.00SG AW = 18g  
95.5% Gold - 1.5% Silver  
3% Copper



Antique Gold 22.75kt  
CR22.75AG AW = 18g  
94.8% Gold - 3.2% Silver  
2% Copper



Caplain 20kt ♦  
CR20.CL/80 AW = 14g  
86% Gold - 5% Silver -  
5% Palladium - 4% Copper



White 9kt ♦  
CR9.00WH AW = 16g  
49% Gold - 51% Silver



Platinum ♦☀  
CR00.00PT AW = 20.9g  
100% Platinum

Loose leaf oil Gilded on white paper. The ♦ indicates leaf that is also available in patent form.

AW = Average total weight (gold + alloy) indicated in grams per 1000 leaves.

The ■ indicates leaf that is available as Ribbon Gold. ☀ Indicates appropriate for exterior use. **See over** ↩



# Gold Leaf German



Platinum White  
CR00.PT/420 AW = 17.5g  
Gold - Silver - Platinum



Platinum Metal White  
CR00.PT/526 AW = 17.5g  
Gold - Silver - Palladium

## General Product Information

Available in various karats, Eytzinger genuine gold leaf is available in the classic loose leaf format (suitable for decorating both carved surfaces with the water gilding technic and smooth surfaces with the oil gilding method); in transfer leaf format (suitable for the decoration of flat surfaces and external gilding, only with the oil gilding technique) and in rolls (genuine gold leaves are laid on a roll of tissue paper, thus forming a continuous of pre-overlapping leaves. Rolls are used for the gilding of large flat surfaces or outdoor decorations).

To discover more of our Eytzinger line, please visit [www.Seppleaf.com](http://www.Seppleaf.com)



Loose leaf oil Gilded on white paper. The ♦ indicates leaf that is also available in patent form.

AW = Average total weight (gold + alloy) indicated in grams per 1000 leaves.

The ■ indicates leaf that is available as Ribbon Gold. ★ Indicates appropriate for exterior use.